

TECHNICAL DATA SHEET

FLOOR BLOCK 4

THERMALITE

a **Forterra** brand





VIEW PRODUCT ONLINE

RELIABLE PERFORMANCE UNDERFOOT

For use in beam and block flooring systems, **Thermalite Floor Block 4** is suitable across a wide range of floor layouts.

Low unit weight supports efficient on-site handling and installation, helping improve productivity during construction. With a design thermal conductivity (protected, 3%) of just 0.16 W/m²K, **Thermalite Floor Blocks** contribute to improved thermal performance, supporting the energy efficiency standards demanded in modern housing.

Thermalite is recognised as a pioneer of aircrete with its closed micro-cellular structure – formed of millions of tiny, trapped air pockets – which allow for lightweight handling and a favourable strength-to-weight ratio.

KEY FACTS

(based on 440x215x100mm block)

Compressive Strength:	4 N/mm²
Weight:	8.3kg/block
Design Thermal Conductivity: Protected (3%)	0.16 W/m.K
Reaction to fire: BS EN 13501	A1

BBA APPROVAL INSPECTION TESTING CERTIFICATION CERTIFICATE 91/2723

UK CA

FLOOR BLOCK 4

THERMALITE
a Forterra brand

PRODUCT APPLICATION

BLOCK WIDTH	CAVITY WALLS EXTERNAL LEAF BELOW DPC	CAVITY WALLS EXTERNAL LEAF ABOVE DPC	CAVITY WALLS INNER LEAF BELOW DPC	CAVITY WALLS INNER LEAF ABOVE DPC	SOLID EXTERNAL WALLS BELOW DPC	SOLID EXTERNAL WALLS ABOVE DPC	SEPARATING WALLS	INTERNAL PARTITIONS	BEAM & BLOCK FLOORING INFILL
100mm	✗	✗	✗	✗	✗	✗	✗	✗	✓

NOTES:

Φ Product suitability in this application is subject to the block achieving the sites soil / groundwater DS classification requirements.

ϑ Blocks in the external leaf from DPC level to 150mm below ground level must not be left exposed, suitable products such as clay bricks of Class B Engineering properties or “F2” durability in accordance with BS EN 771-1 should be specified in this zone, alternatively blocks may be covered with a suitable protective finish.

Ϫ For all external leaf applications, the block requires a suitable impervious coating or finish applied, blocks must not be left exposed when used on the external leaf.

Ж Product suitability in this application is subject to the block achieving the walls specification requirements for sound reduction or those specification criteria set in the Robust Detail selected.

Products should be designed and constructed in accordance with all relevant Legislation, Building Regulations, European & British Standards, Acts, Codes of Practice and manufacturers recommendations.

Please refer to Building Regulations, Approved Document A and the Projects Structural Engineer for minimum wall thickness, block compressive strength and characteristic strength requirements - specification varies subject to numerous factors which include loading, block orientation, restraint, wall height and length.

If you are considering applying a render or cladding, please contact the finish supplier for block/brick suitability.

Block weights based on gross density @ 23% moisture content, moisture equilibrium approximately 3% (protected) and 5% (exposed).

FLOOR BLOCK 4

THERMALITE
a Forterra brand

PRODUCT TECHNICAL DATA

Width (mm):	100
Face Sizes – L x H (mm):	440 x 215
Dimensional Tolerance Classification:	GPLM
Dimensional Tolerance – Length:	(+3mm -5mm)
Dimensional Tolerance – Height:	(+3mm -5mm)
Dimensional Tolerance – Width:	(+3mm -3mm)
Unit Weight, Gross Density @ 23% Moisture (kg):	7.7
Configuration:	Group 1 (Solid)
Category:	II
Mean Compressive Strength (N/mm^2): The declared properties are based on the block being laid in their intended orientation i.e. face size (L x H) and thickness stated on this technical data sheet. Please contact Forterra for further information before using the block in a different orientation.	4
Gross Dry Density (kg/m^3):	660
Thermal Conductivity - λ10, dry unit, S2 (W/m.K)	0.140
Design Thermal Conductivity - Protected (3%) (W/m.K):	0.160
Design Thermal Conductivity - Exposed (5%) (W/m.K):	0.175
Design Thermal Conductivity - (15%) (W/m.K):	0.26
Thermal Resistance - Protected (3%) (m^2.K/W):	0.62
Thermal Resistance - Exposed (5%) (m^2.K/W):	0.57
Sound Reduction – Unfinished (RW dB): Sound Reduction - Calculated based on unfinished. On-site testing values may be lower.	NPD
Fire Resistance (Hours) (NA to BS EN 1996-1-2) – Non-load Bearing Single Leaf walls (Criteria EI):	NPD
Fire Resistance (Hours) (NA to BS EN 1996-1-2) – Load Bearing Single Leaf walls (Criteria REI) ≤ 0.7:	NPD
Load Bearing Single Leaf walls (Criteria REI) ≤ 0.42:	NPD
Reaction to Fire (BS EN 13501):	A1
Water Vapor Permeability:	5/10
Dimensional Stability - Moisture Movement (mm/m):	nominal 0.5
Vapour Resistivity (MN.s/g.m):	50
Soil or Groundwater DS Classification:	DS 1-4
Shear Bond Strength (N/mm^2):	0.15
Third Party Certification:	Yes (BBA Certificate 91/2723 - Product Sheet 1)
Movement Joint Detail	Vertical movement joints at no more than 6m centres and not more than half that spacing from a corner

Blocks are manufactured to BS EN 771-4. NPD denotes 'No Performance Declaration'; please contact Forterra for further information.

Forterra Design & Technical Services
Atherstone Road, Measham, Derbyshire DE12 7EL
Tel: +44 (0) 330 123 1018
Email: asktechnical@forterra.co.uk
forterra.co.uk

Version 3 (Last published: 21/08/2026)
Valid at the time of publication. Please check our website (www.forterra.co.uk) for the latest product information and documentation. For previous versions please contact us.

FORTERRA